

الترجمة الفنية: راجع الرسومات الأصلية والصفحات المرجعية لمعرفة الأبعاد.

صفحة المصدر 1

ورقة بيانات المنتج

الشركة المصنعة لأنظمة الملفات الشخصية Mox

عنوان الوثيقة التصميم والجودة: Revio

اسم المنتج موكس ريفيو

وصف المنتج حافة السجاد الألومنيوم

رقم الصنف RVO

مجال الاستخدام عام، مكتب، سكني

المواد EN AW 6463 T6، EN AW 6061 T6

الطول 8'

السطح بأكسيد

تم تصميم حافة السجاد المصنوعة من الألومنيوم Revio خصيصا لزيادة جمالية ووظيفة الأرضية الخاصة بك.

لا يوفر شكل حافة السجاد المصنوع من الألومنيوم Revio انتقالا سلسا بين أسطح الأرضيات المختلفة فحسب، بل يحمي أيضا حواف سجادتك، ويمنع التآكل والتشوه الذي قد يحدث بمرور الوقت.

تساعدك ملفات التعريف هذه على تقليل تكاليف الإصلاح والاستبدال من خلال إطالة عمر سجادتك.

يتميز بمتانة عالية وعمر افتراضي طويل، حيث صنع من مواد خام فائقة الجودة ويتمتع بجدران سميكة.

على عكس منافسيها، فهي تتميز بسمك الطلاء وجودة الأنودة.

يتميز بمظهر أنيق وعصري بشكله البسيط ويسهل الانتقال بين الطوابق.

تتميز حافة السجاد المصنوعة من الألومنيوم Revio بأنها سهلة الاستخدام أثناء مرحلة التثبيت، مما يسمح لك بتحقيق نتيجة احترافية في وقت قصير من خلال تعليمات واضحة وأدوات بسيطة.

يمكن تنفيذ الزوايا عن طريق قص القطع بزاوية 45 درجة.

تتميز حافة السجاد المصنوعة من الألومنيوم Revio بخيار طلاء مؤكسد غير لامع باللون الفضي والأصفر والإينوكس.

الصفحة 1/2

الضمان

هذا المنتج تحت الضمان لمدة 5 سنوات من تاريخ الاستلام باستثناء أخطاء المستخدم كما هو موضح أدناه:

الأضرار الناجمة عن الاصطدام الأضرار الناجمة عن الخدش الأضرار الناجمة عن ملامسة المادة الكاشطة أو عوامل التنظيف

الكيميائية الأضرار الناجمة عن التلامس المطول مع الماء الأضرار الناجمة عن التعرض لدرجة الحرارة الشديدة الأضرار الناجمة عن التركيب

LANOITANRETN FORANODISING QualityLABEL INDUSTRIAL TS-EN 755-8 TS-EN 755-9 TS 4922


الرسومات الأصلية والصفحات المرجعية

Product Datasheet



Manufacturer	Mox Profile Systems
Document Title	Design and quality: Revio
Product Name	Revio
Product Description	Aluminium Carpet Edge Profile
Item No	RVO
Area of Use	Public, Office, Residential
Material	EN AW 6463 T6, EN AW 6061 T6
Length	8'
Surface	Anodised

Revio aluminum carpet edge profile is specially designed to increase the aesthetics and functionality of your floor. Revio aluminum carpet edge profile not only provides a seamless transition between different flooring surfaces, but also protects the edges of your carpet, preventing wear and deformation that may occur over time. These profiles help you reduce repair and replacement costs by extending the life of your carpet. It is extremely durable and long-lasting since it is produced from high quality raw material and has thick walls. Unlike its competitors, it stands out with its coating thickness and quality of anodizing. It has a stylish and modern appearance with its oval form and facilitates the transition between floors. Revio aluminum carpet edge profile is user-friendly during the installation phase, allowing you to achieve a professional result in a short time with clear instructions and simple tools. Corners can be assembled by cutting profile to 45 degree. Revio aluminum carpet edge profile has a matte anodized coating option in silver, yellow and inox colors.



Warranty

This product is under warranty for 5 years from the date of receipt except for the user errors as listed below:

- Damage caused by impact
- Damage caused by scratching
- Damage caused by abrasive substance or chemical cleaning agents contact
- Damage caused by prolonged contact with water
- Damage caused by exposure to intense temperature
- Damage caused by montage



ALLOY DATASHEET

EN AW 6463 T6 [AlMg0.7Si]

Place Of Use

The alloy EN AW-6463 is a widely used extrusion alloy, suitable for applications where only modest strength properties are required. Parts can be produced with a good surface quality, suitable for many coating operations. Typical application fields are furniture, finishing materials, windows and doors, car body finishing, facade construction, lighting columns and flagpoles.

Chemical composition according to EN573-3 (weight%, remainder Al)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0,20 - 0,60	Max 0,15	0,2	Max 0,5	0,45 - 0,9	-	Max 0,05	Max 0,1	Rest

Mechanical properties according to EN755-2

Temper*	Wall Thickness e***	Yield Stress	Tensile Strength	Elongation	Brinell Hardness
-	e* mm	Rp0,2 min Mpa	Rm min Mpa	Min A50mm % - Max A %	HB**
T4	e≤50	75	125	14 - 12	46
T5	e≤50	150	110	8 - 6	60
T6	e≤50	195	160	10 - 8	74

* Temper designation according to EN515: T4-Naturally aged to a stable condition, T5-cooled from an elevated temperature forming operation and artificially aged, T6-Solution heat treated, quenched and artificially aged,

** Hardness values are for indication only,

*** For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section.

Physical properties (approximate values, 20°C)

Density (kg/m³)	Melting range (°C)	Electrical conductivity (MS/m)	Thermal conductivity (W/m.K)	Co-efficient of thermal expansion 10 ⁻⁶ /K	Modulus of elasticity (GPa)
2700	585-650	28-34	200-220	23.4	~70

Weldability¹

Gas: 3 TIG: 2 MIG: 2

Typical filler materials (EN ISO18273): SG-AlMg5Cr(A) or AlSi5, and AlMg3 when the product has to be anodised. Due to the heat input during welding the mechanical properties will be reduced by approximately 50% (ref. EN1999-1).

Machining characteristics¹: T4 Temper 3 / T5, T6 Temper 2

Coating properties¹ Hard/protective anodising: 1 / Decorative / bright / colour anodising: 2

Corrosion resistance¹ General: 1 Marine: 2

¹Relative qualification ranging from 1-very good to 6-unsuitable