

الترجمة الفنية: راجع الرسومات الأصلية والصفحات المرجعية لمعرفة الأبعاد.

صفحة المصدر 1

ورقة بيانات المنتج

الشركة المصنعة لأنظمة الملفات الشخصية MOX

عنوان الوثيقة التصميم والجودة: Visio

اسم المنتج موكس فيسيو

وصف المنتج عتبة السجاد الألومنيوم

رقم الصنف VSO

مجال الاستخدام عام، مكتب، سكني

المواد EN AW 6463 T6، EN AW 6061 T6

الطول 2500 مم

السطح بأكسيد

توفر عتبة السجاد المصنوعة من الألومنيوم Visio انتقالات داخلية آمنة وجمالية وطويلة الأمد بين مواد الأرضيات المختلفة.

إنها تخلق بيئة آمنة، خاصة للأطفال وكبار السن، من خلال توفير انتقال سلس بين ارتفاعات الأرضيات المختلفة.

تم تصميم عتبة السجاد المصنوعة من الألومنيوم Visio لسد الفجوات بين السجاد وأغطية الأرضيات الأخرى.

فهو يوفر انتقالاً سلساً بين السجاد وأنواع أغطية الأرضيات الأخرى، مما يزيل أي مخالفات أو مخاطر التعثر التي قد تحدث.

كما أنه يطيل عمر السجاد من خلال حمايته من التآكل.

يعمل Visio، الذي يتمتع بمظهر جمالي بالإضافة إلى مزايا وظيفية، على تحسين المظهر العام لتصميمك الداخلي.

يتميز بمتانة عالية وعمر افتراضي طويل، حيث صنع من مواد خام فائقة الجودة ويتمتع بجدران سميكة.

على عكس منافسيها، فهي تتميز بسمك الطلاء وجوده الأنودة.

في حين أنه يوفر مظهراً عصرياً بتصميمه المسنن، فإنه يمنع الحوادث غير المرغوب فيها بفضل ميزة عدم الانزلاق.

وفي الوقت نفسه، يساعد تصميمه البيضاوي على إخفاء العيوب في مفاصل الأرضية.

يمكن تركيب عتبة السجاد المصنوعة من الألومنيوم Visio بسهولة عن طريق وضع لاصق البلاط على وصلات الوصلات.

يمكن تنفيذ الزوايا عن طريق قص القطع بزاوية 45 درجة.

يتميز شكل عتبة السجاد المصنوع من الألومنيوم Visio بخيار طلاء مؤكسد غير لامع باللون الفضي والأصفر والإينوكس.

الصفحة 1/2

الضمان

هذا المنتج تحت الضمان لمدة 5 سنوات من تاريخ الاستلام باستثناء أخطاء المستخدم كما هو موضح أدناه:

الأضرار الناجمة عن الاستخدام الأضرار الناجمة عن الخدش الأضرار الناجمة عن ملامسة المادة الكاشطة أو عوامل التنظيف

الكيميائية الأضرار الناجمة عن التلامس المطول مع الماء الأضرار الناجمة عن التعرض لدرجة الحرارة الشديدة الأضرار الناجمة عن

التركيب

LANOITANRETNi FORANODISING QualityLABEL INDUSTRIAL TS-EN 755-8 TS-EN 755-9 TS 4922

صفحة المصدر 2

ورقة بيانات السبائك

EN AW 6463 T6 [AlMg0.7Si]

مكان الاستخدام

إن السبيكة EN AW-6463 عبارة عن سبيكة بثق مستخدمة على نطاق واسع، ومناسبة للتطبيقات التي تتطلب خصائص قوة متواضعة فقط.

يمكن أن تكون الأجزاء

تم إنتاجه بجودة سطحية جيدة ومناسبة للعديد من عمليات الطلاء.

مجالات التطبيق النموذجية هي الأثاث ومواد التشطيب والنوافذ والأبواب،

تشطيب هياكل السيارات وبناء الواجهات وأعمدة الإنارة وساريات الأعلام.

التركيب الكيميائي طبقا للمواصفة EN573-3 (الوزن %، الباقي Al)

سي الحديد النحاس المنغنيز الكروم الزنك تي آل

0,20 - 0,60 الحد الأقصى 0,15 0,2 الحد الأقصى 0,5 0,45 - 0,9 الحد الأقصى 0,05 الحد الأقصى 0,1 الراحة

الخواص الميكانيكية حسب EN755-2

المزاج* سمك الجدار ***e إجهاد الخضوع قوة الشد الاستطالة صلابة برينل

- e* مم Rp0,2 دقيقة ميغا باسكال Rm دقيقة ميغا باسكال A50 مم % - الحد الأقصى HB % **A

T4 e ≥ 50 75 125 14 - 12 46

T5 e ≥ 50 150 110 8 - 6 60

T6 e ≥ 50 195 160 10 - 8 74

* تصنيف الحالة المعدنية وفقا للمواصفة T4: EN515-تعتيق طبيعي للوصول إلى حالة مستقرة، T5-تبريد بعد عملية تشكيل عند درجة حرارة مرتفعة و

تعتيق اصطناعي، T6-معالجة حرارية بالإذابة، ثم تبريد سريع وتعتيق اصطناعي،

** قيم الصلابة للإشارة فقط،

*** بالنسبة لسماكات الجدار المختلفة ضمن مقطع واحد، يجب اعتبار أقل الخصائص المحددة صالحة للمقطع العرضي للملف بأكمله.

الخصائص الفيزيائية (القيم التقريبية، 20 درجة مئوية)

نطاق ذوبان الكثافة الحرارية الكهربائية ذات الكفاءة المشتركة لمعامل

(كجم/م³) (درجة مئوية) الموصلية الموصلية المرونة الحرارية

2700 650-585 (مللي ثانية/م) (وات/م.ك) التوسع (المعدل التراكمي)

28-34 200-220 10⁻⁶/ك 70~

قابلية اللحام¹

غاز: 3 تيج: 2 ميغ: 2

مواد الحشو المعتادة (EN ISO18273): SG-AlMg5Cr(A) أو AlSi5، وAlMg3 عندما يتطلب المنتج معالجة بالأنودة.

بسبب مدخلات الحرارة أثناء اللحام

سيتم تقليل الخواص الميكانيكية بنسبة 50% تقريبا (المرجع).

EN1999-1).

خصائص التصنيع¹: درجة الحرارة 3 T4 / درجة الحرارة T5، درجة الحرارة 2 T6

خصائص الطلاء¹ أنودة صلبة/واقية: 1 / أنودة زخرفية / ساطعة / ملونة: 2

مقاومة التآكل¹ عام: 1 بحري: 2

¹المؤهل النسبي يتراوح من 1-جيد جدا إلى 6-غير مناسب

صفحة 2/2


الرسومات الأصلية والصفحات المرجعية

Product Datasheet



Manufacturer	Mox Profile Systems
Document Title	Design and quality: Visio
Product Name	Visio
Product Description	Aluminium Carpet Threshold Profile
Item No	VSO
Area of Use	Public, Office, Residential
Material	EN AW 6463 T6, EN AW 6061 T6
Length	2500mm
Surface	Anodised

Visio aluminum carpet threshold profile provides safe, aesthetic and long-lasting interior transitions between different flooring materials. It creates a safe environment, especially for children and the elderly, by providing a smooth transition between different flooring heights. Visio aluminum carpet threshold profile is designed to close gaps between carpet and other floor coverings. It provides a smooth transition between carpet and other floor covering types, eliminating any irregularities or tripping hazards that may occur. It also prolongs the life of carpets by protecting them against wear and tear. Visio, which has an aesthetic appearance as well as functional advantages, improves the overall appearance of your interior design. It is extremely durable and long-lasting since it is produced from high quality raw material and has thick walls. Unlike its competitors, it stands out with its coating thickness and quality of anodizing. While it provides a modern appearance with its serrated design, it prevents unwanted accidents thanks to its non-slip feature. At the same time, its oval design helps hide defects at floor joints. Visio aluminum carpet threshold profile can be easily installed by applying tile adhesive to the joints extensions. Corners can be assembled by cutting profile to 45 degree. Visio aluminum carpet threshold profile has a matte anodized coating option in silver, yellow and inox colors.



Warranty

This product is under warranty for 5 years from the date of receipt except for the user errors as listed below:

- Damage caused by impact
- Damage caused by scratching
- Damage caused by abrasive substance or chemical cleaning agents contact
- Damage caused by prolonged contact with water
- Damage caused by exposure to intense temperature
- Damage caused by montage



ALLOY DATASHEET
EN AW 6463 T6 [AlMg0.7Si]

Place Of Use

The alloy EN AW-6463 is a widely used extrusion alloy, suitable for applications where only modest strength properties are required. Parts can be produced with a good surface quality, suitable for many coating operations. Typical application fields are furniture, finishing materials, windows and doors, car body finishing, facade construction, lighting columns and flagpoles.

Chemical composition according to EN573-3 (weight%, remainder Al)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0,20 - 0,60	Max 0,15	0,2	Max 0,5	0,45 - 0,9	-	Max 0,05	Max 0,1	Rest

Mechanical properties according to EN755-2

Temper*	Wall Thickness e***	Yield Stress	Tensile Strength	Elongation	Brinell Hardness
-	e* mm	Rp0,2 min Mpa	Rm min Mpa	Min A50mm % - Max A %	HB**
T4	e≤50	75	125	14 - 12	46
T5	e≤50	150	110	8 - 6	60
T6	e≤50	195	160	10 - 8	74

* Temper designation according to EN515: T4-Naturally aged to a stable condition, T5-cooled from an elevated temperature forming operation and artificially aged, T6-Solution heat treated, quenched and artificially aged,

** Hardness values are for indication only,

*** For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section.

Physical properties (approximate values, 20°C)

Density (kg/m³)	Melting range (°C)	Electrical conductivity (MS/m)	Thermal conductivity (W/m.K)	Co-efficient of thermal expansion 10 ⁻⁶ /K	Modulus of elasticity (GPa)
2700	585-650	28-34	200-220	23.4	~70

Weldability¹

Gas: 3 TIG: 2 MIG: 2

Typical filler materials (EN ISO18273): SG-AlMg5Cr(A) or AlSi5, and AlMg3 when the product has to be anodised. Due to the heat input during welding the mechanical properties will be reduced by approximately 50% (ref. EN1999-1).

Machining characteristics¹: T4 Temper 3 / T5, T6 Temper 2

Coating properties¹ Hard/protective anodising: 1 / Decorative / bright / colour anodising: 2

Corrosion resistance¹ General: 1 Marine: 2

¹Relative qualification ranging from 1-very good to 6-unsuitable