

MOX Systems - tehnička dokumentacija

datasheet-velo-en.pdf

Tehnički prijevod: konsultujte originalne crteže i referentne stranice za dimenzije.

Izvorna stranica 1

Tehnički list proizvoda

Proizvođač Mox Profile Systems

Naslov dokumenta Dizajn i kvaliteta: Velo

Naziv proizvoda Velo

Opis proizvoda Aluminijska lajsna

Artikl br. VLO

Područje upotrebe Javno, Uredsko, Stambeno

Materijal EN AW 6463 T6, EN AW 6061 T6

Dužina 2500mm

Površinski obložen prahom, eloksiran, hromiran

Velo aluminijska lajsna pruža rešenja za lajsne posebno za vlažne prostore kao što su kupatila i kuhinje.

Zauzima manje prostora i nudi jednostavnu instalaciju.

Pružza zaštitu od curenja kao i estetiku pokrivajući defekte spojeva zid-pod, posebno na vlažnim prostorima.

Može se koristiti za ovalne zidne aplikacije jer je pogodan za savijanje.

Izuzetno je izdržljiv i dugotrajan jer je proizveden od visokokvalitetnih sirovina i ima debele stijenke.

Za razliku od svojih konkurenata, ističe se debljinom premaza i kvalitetom eloksiranja, te primjenom predtretmana koja osigurava otpornost na koroziju kod elektrostatičkog praškastog farbanja.

Velo pruža izgled u ravni sa zidom i ne uzrokuje gubitak prostora.

Velo aluminijska lajsna se lako postavlja direktnim nanošenjem lepka.

Uglovi se mogu sastaviti rezanjem profila na 45 stepeni.

Velo aluminijska lajsna ima mat eloksirane, svijetle eloksirane, satenske kemijske svijetle anodizirane i elektrostatičke boje u prahu.

Dok su dostupni srebrni, žuti, inox, bronzani i crni eloksirani premazi u boji, može se farbati i prema željenom RAL kodu elektrostatičkim praškastim farbanjem.

Stranica 1/2

Garancija

Ovaj proizvod je pod garancijom 5 godina od datuma prijema osim za greške korisnika kao što su navedene u nastavku:

Oštećenja uzrokovana udarom Oštećenja uzrokovana grebanjem Oštećenja uzrokovana kontaktom abrazivnih tvari ili kemijskih sredstava za čišćenje Oštećenja uzrokovana produženim kontaktom s vodom Oštećenja uzrokovana izlaganjem visokoj temperaturi Oštećenja uzrokovana montažom

LANOITANRETN FORANODIZACIJSKA OZNAKA KVALITETA INDUSTRIJSKA TS-EN 755-8 TS-EN 755-9 TS 4922

Izvorna stranica 2

ALLOY DATASHEET

EN AW 6463 T6 [AlMg0.7Si]

Mjesto upotrebe

Legura EN AW-6463 je široko rasprostranjena legura za ekstruziju, pogodna za primjene gdje su potrebna samo skromna svojstva čvrstoće.

Dijelovi mogu biti

proizveden s dobrim kvalitetom površine, pogodan za mnoge operacije premazivanja.

Tipična područja primjene su namještaj, završni materijali, prozori i vrata,

dorada karoserije automobila, izrada fasada, rasvjetni stubovi i jarboli.

Hemijski sastav prema EN573-3 (težina%, ostatak Al)

Si Fe Cu Mn Mg Cr Zn Ti Al

0,20 - 0,60 Max 0,15 0,2 Max 0,5 0,45 - 0,9 - Max 0,05 Max 0,1 Ostalo

Mehanička svojstva prema EN755-2

Temperatura* Debljina stijenke e*** Napon tečenja Vlačna čvrstoća Izduženje Tvrdća po Brinelu

- e* mm Rp0,2 min Mpa Rm min Mpa Min A50mm % - Max A % HB**

T4 e≤50 75 125 14 - 12 46

T5 e≤50 150 110 8 - 6 60

T6 e≤50 195 160 10 - 8 74

* Oznaka temperameta prema EN515: T4-prirodno ostario u stabilno stanje, T5-ohlađen od operacije oblikovanja na povišenoj temperaturi i

umjetno odležano, T6-Solution termički obrađeno, kaljeno i umjetno odležano,

** Vrijednosti tvrdoće su samo indikativne,

*** Za različite debljine zida unutar jednog profila, najniža specificirana svojstva će se smatrati važećim za cijeli poprečni presjek profila.

Fizička svojstva (približne vrijednosti, 20°C)

Gustina Opseg topljenja Električni toplinski koeficijent modula od

(kg/m³) (°C) provodljivost provodljivost toplotna elastičnost

2700 585-650 (MS/m) (W/m.K) ekspanzija (GPa)

28-34 200-220 10⁻⁶/K ~70

Zavarljivost¹

Gas: 3 TIG: 2 MIG: 2

Tipični materijali za punjenje (EN ISO18273): SG-AlMg5Cr(A) ili AlSi5 i AlMg3 kada se proizvod mora anodizirati.

Zbog unosa topline tokom zavarivanja

mehanička svojstva će se smanjiti za približno 50% (ref.

EN1999-1).

Karakteristike obrade¹: T4 Temper 3 / T5, T6 Temper 2

Svojstva premaza¹ Tvrd/zaštitno eloksiranje: 1 / Dekorativno / svijetlo / eloksiranje u boji: 2

Otpornost na koroziju¹ Općenito: 1 Pomorski: 2

¹Relativna kvalifikacija u rasponu od 1-veoma dobro do 6-neprikladno

Strana 2/2



Originalni crteži i referentne stranice

Product Datasheet



Manufacturer	Mox Profile Systems
Document Title	Design and quality: Velo
Product Name	Velo
Product Description	Aluminium Skirting Board
Item No	VLO
Area of Use	Public, Office, Residential
Material	EN AW 6463 T6, EN AW 6061 T6
Length	2500mm
Surface	Powder Coated, Anodised, Chrome Plated

Velo aluminium skirting board provides skirting solutions especially for wet areas like bathrooms and kitchens. It takes up less space and offers ease of installation. It provides leak proofing as well as aesthetics by covering the wall-floor joint defects especially on wet areas. It can be used in oval wall applications as it is suitable for bending. It is extremely durable and long-lasting since it is produced from high quality raw material and has thick walls. Unlike its competitors, it stands out with its coating thickness and quality of anodizing, and with its pretreatment application that provides resistance to corrosion in electrostatic powder painting. Velo provides a flush appearance with the wall and does not cause any loss of space. Velo aluminium skirting board can be easily installed by directly applying adhesive. Corners can be assembled by cutting the profile to 45 degrees. Velo aluminium skirting board has matte anodized, bright anodized, satin chemical bright anodized and electrostatic powder painting options. While silver, yellow, inox, bronze and black anodized color coatings are available, it can also be painted to the desired RAL code with electrostatic powder painting.



ALLOY DATASHEET

EN AW 6463 T6 [AlMg0.7Si]

Place Of Use

The alloy EN AW-6463 is a widely used extrusion alloy, suitable for applications where only modest strength properties are required. Parts can be produced with a good surface quality, suitable for many coating operations. Typical application fields are furniture, finishing materials, windows and doors, car body finishing, facade construction, lighting columns and flagpoles.

Chemical composition according to EN573-3 (weight%, remainder Al)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0,20 - 0,60	Max 0,15	0,2	Max 0,5	0,45 - 0,9	-	Max 0,05	Max 0,1	Rest

Mechanical properties according to EN755-2

Temper*	Wall Thickness e***	Yield Stress	Tensile Strength	Elongation	Brinell Hardness
-	e* mm	Rp0,2 min Mpa	Rm min Mpa	Min A50mm % - Max A %	HB**
T4	e≤50	75	125	14 - 12	46
T5	e≤50	150	110	8 - 6	60
T6	e≤50	195	160	10 - 8	74

* Temper designation according to EN515: T4-Naturally aged to a stable condition, T5-cooled from an elevated temperature forming operation and artificially aged, T6-Solution heat treated, quenched and artificially aged,

** Hardness values are for indication only,

*** For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section.

Physical properties (approximate values, 20°C)

Density (kg/m³)	Melting range (°C)	Electrical conductivity (MS/m)	Thermal conductivity (W/m.K)	Co-efficient of thermal expansion 10 ⁻⁶ /K	Modulus of elasticity (GPa)
2700	585-650	28-34	200-220	23.4	~70

Weldability¹

Gas: 3 TIG: 2 MIG: 2

Typical filler materials (EN ISO18273): SG-AlMg5Cr(A) or AlSi5, and AlMg3 when the product has to be anodised. Due to the heat input during welding the mechanical properties will be reduced by approximately 50% (ref. EN1999-1).

Machining characteristics¹: T4 Temper 3 / T5, T6 Temper 2

Coating properties¹ Hard/protective anodising: 1 / Decorative / bright / colour anodising: 2

Corrosion resistance¹ General: 1 Marine: 2

¹Relative qualification ranging from 1-very good to 6-unsuitable