

MOX Systems - doiciméadú teicniúil

datasheet-sole-us-en.pdf

Aistriúchán teicniúil: féach ar na bunlíneacha agus ar na leathanaigh thagartha le haghaidh toisí.

Leathanach foinse 1

Bileog Sonraí Táirge

Córais Próifíl Mox Monaróir

Teideal an Doiciméid Dearadh agus cáilíocht: Sole

Ainm Táirge Sole

Cur síos ar an Táirge Bord Sciorta Alúmanam

Mír Uimh SOL

Réimse Úsáide Poiblí, Oifige, Cónaithe

Ábhar EN AW 6463 T6, GA AW 6061 T6

Fad 8'

Púdar Dromchla Brataithe, Anodised, Chrome Plátáilte

Is fearr próifíl bord sciorta alúmanaim Sole den chuid is mó i ngach áit mhaireachtála agus limistéar poiblí le dearadh dearadh clasaiceach. Clúdaíonn sé na lochtanna sna hailt urláir agus balla.

Cuireann sé cosc ar charnadh salachar agus orgánaigh dhochracha úsáid shláintiúil agus shláintiúil a sholáthar le blianta fada.

Agus an limistéar log ina dhearadh, bailíonn sé na cáblaí teileafóin, leictreachais agus idirlín chun do thimpeallacht a eagrú.

Tá sé thar a bheith durable agus fada buan ós rud é go ndéantar é a tháirgeadh ó amháibhar ardchaighdeán agus go bhfuil ballaí tiubh aige.

Murab ionann agus a chuid iomaitheoirí, seasann sé amach lena tiús sciath agus cáilíocht anodizing, agus lena iarratas réamhchóireála a sholáthraíonn friotaíocht creimeadh i bpéintéireacht púdar leictreastatach.

Dearadh Sole do gach spás maireachtála clasaiceach, luxurious agus mór le rá.

Is féidir próifíl bord sciorta alúmanaim Sole a shuiteáil go héasca tríd an bpíosa cúil uilíoch a shocrú leis an mballa le scriúnná agus an próifíl clúdach tosaigh a fheistiú lena chóras glas Léim. Is féidir coirnéil a chur le chéile trí phróifíl a ghearradh go 45 céim.

Tá sé ar fáil i fad 2500mm agus airde 100mm.

Tá roghanna péinteála púdar anodized agus leictreastatacha ag bord sciorta alúmanaim Sole.

Cé go bhfuil bratuithe dath anodized airgid ar fáil, is féidir é a phéinteáil freisin chuig an gcód RAL atá ag teastáil le péintéireacht púdar leictreastatach.

Leathanach 1/2

Bharántas

Tá an táirge seo faoi bharántas ar feadh 5 bliana ón dáta fála ach amháin i gcás na n-earráidí úsáideora mar a liostaítear thíos:

Damáiste de bharr tionchair Damáiste de bharr scríobadh Damáiste de bharr teagmhála le substaint scríobach nó oibreáin ghlantacháin cheimiceacha Damáiste de bharr teagmháil fhada le huisce Damáiste

de bharr nochtadh do theocht dhian Damáiste de bharr montáis

LANOITANRETNÍ FORANOISING CÁILÍOCHTLIPÉAL TIONSCAIL TS-GA 755-8 TS-GA 755-9 TS 4922

Leathanach foinse 2

BILEOG SONRAÍ ALLOY

GA AW 6463 T6 [AlMg0.7Si]

Áit Úsáide

Is cóimhiotal easbhrúite é an cóimhiotal EN AW-6463 a úsáidtear go forleathan, atá oiriúnach d'iarratais nach dteastaíonn ach airíonna neart measartha.

Is féidir le codanna a bheith

a tháirgtear le caighdeán maith dromchla, oiriúnach le haghaidh go leor oibríochtaí sciath.

Is iad na gnáthréimsí feidhmchláir ná troscán, ábhair chríochnaithe, fuinneoga agus doirse, bailchríoch carr-charr, tógáil aghaidheanna, colúin soilsithe agus cuailí bratach.

Comhdhéanamh ceimiceach de réir EN573-3 (meáchan%, fuílleach Al)

Si Fe Cu Mn Mg Cr Zn Ti Al

0,20 - 0,60 Uasmhéid 0,15 0,2 Uasmhéid 0,5 0,45 - 0,9 - Uasmhéid 0,05 Uasmhéid 0,1 Sos

Airíonna meicniúla de réir EN755-2

Teocht* Tiús an Bhalla e*** Strus Toradh Neart Teanntachta Fadú Brinell Cruas

- e* mm Rp0,2 nóim Mpa Rm nó Min Mpa A50mm % - Uasta A % HB**

T4 e≤50 75 125 14 - 12 46

T5 e≤50 150 110 8 - 6 60

T6 e≤50 195 160 10 - 8 74

* Ainmniú teochta de réir EN515: T4-Aois nádúrtha go riocht cobhsaí, T5-cooled ó oibríocht fhoirmiú teocht ardaithe agus

d'aois go saorga, teaschoireáil T6-Solution, múchta agus aois shaorga,

** Is le haghaidh tásc amháin atá luachanna cruas,

*** I gcás tiús bhallaí éagsúla laistigh d'aon phróifíl amháin, measfar go bhfuil na hairíonna sonraithe is ísle bailí do thrasghearradh iomlán na próifíle.

Airíonna fisiceacha (neasluchanna, 20°C)

Dlús Raon Leáphointe Leictreach Teirmeach Comhéifeacht de Modulus de

(kg/m³) (°C) seoltacht seoltacht leaisteachas teirmeach

2700 585-650 (MS/m) (W/m.K) leathnú (GPa)

28-34 200-220 10⁻⁶/K ~70

Táthú¹

Gás: 3 TIG: 2 MIG:2

Ábhair líonta tipiciúla (EN ISO18273): SG-AlMg5Cr(A) nó AlSi5, agus AlMg3 nuair is gá an táirge a anóidiú.

Mar gheall ar an ionchur teasa le linn táthú an

déanfar airíonna meicniúla a athchur faoi thart ar 50% (tag.

EN1999-1).

Saintréithe meaisínithe¹: T4 Teocht 3 / T5, T6 Teocht 2

Airíonna brataithe¹ Anóidiú crua/cosanta: 1 / Maisiúil / geal / anóidiú datha: 2

Friotaíocht chreimeadh¹ Ginearálta: 1 Mara: 2

¹Cáilíocht choibhneasta ó 1 - an-mhaith go 6 mhí-oiriúnach

Leathanach 2/2

Líníochtaí bunaidh agus leathanaigh tagartha

Product Datasheet



Manufacturer	Mox Profile Systems
Document Title	Design and quality: Sole
Product Name	Sole
Product Description	Aluminium Skirting Board
Item No	SOL
Area of Use	Public, Office, Residential
Material	EN AW 6463 T6, EN AW 6061 T6
Length	8'
Surface	Powder Coated, Anodised, Chrome Plated

Sole aluminum skirting board profile is mostly preferred in all living areas and public areas with classical design concepts. It covers the defects in floor and wall joints. It prevents dirt accumulation and harmful organisms to provide hygienic and healthy use for many years. With the hollow area in its design, it collects the telephone, electricity and internet cables to organize your environment. It is extremely durable and long-lasting since it is produced from high quality raw material and has thick walls. Unlike its competitors, it stands out with its coating thickness and quality of anodizing, and with its pre-treatment application that provides resistance to corrosion in electrostatic powder painting. Sole was designed for all classical, luxurious and prestigious living spaces. Sole aluminum skirting board profile can be easily installed by fixing the universal rear piece to the wall with screws and mounting the front cover profile with its snap lock system. Corners can be assembled by cutting profile to 45 degree. It is available in 2500mm length and 100mm height. Sole aluminum skirting board has matte anodized and electrostatic powder painting options. While silver anodized color coatings is available, it can also be painted to the desired RAL code with electrostatic powder painting.



Warranty

This product is under warranty for 5 years from the date of receipt except for the user errors as listed below:

- Damage caused by impact
- Damage caused by scratching
- Damage caused by abrasive substance or chemical cleaning agents contact
- Damage caused by prolonged contact with water
- Damage caused by exposure to intense temperature
- Damage caused by montage



ALLOY DATASHEET

EN AW 6463 T6 [AlMg0.7Si]

Place Of Use

The alloy EN AW-6463 is a widely used extrusion alloy, suitable for applications where only modest strength properties are required. Parts can be produced with a good surface quality, suitable for many coating operations. Typical application fields are furniture, finishing materials, windows and doors, car body finishing, facade construction, lighting columns and flagpoles.

Chemical composition according to EN573-3 (weight%, remainder Al)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0,20 - 0,60	Max 0,15	0,2	Max 0,5	0,45 - 0,9	-	Max 0,05	Max 0,1	Rest

Mechanical properties according to EN755-2

Temper*	Wall Thickness e***	Yield Stress	Tensile Strength	Elongation	Brinell Hardness
-	e* mm	Rp0,2 min Mpa	Rm min Mpa	Min A50mm % - Max A %	HB**
T4	e≤50	75	125	14 - 12	46
T5	e≤50	150	110	8 - 6	60
T6	e≤50	195	160	10 - 8	74

* Temper designation according to EN515: T4-Naturally aged to a stable condition, T5-cooled from an elevated temperature forming operation and artificially aged, T6-Solution heat treated, quenched and artificially aged,

** Hardness values are for indication only,

*** For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section.

Physical properties (approximate values, 20°C)

Density (kg/m³)	Melting range (°C)	Electrical conductivity (MS/m)	Thermal conductivity (W/m.K)	Co-efficient of thermal expansion 10 ⁻⁶ /K	Modulus of elasticity (GPa)
2700	585-650	28-34	200-220	23.4	~70

Weldability¹

Gas: 3 TIG: 2 MIG: 2

Typical filler materials (EN ISO18273): SG-AlMg5Cr(A) or AlSi5, and AlMg3 when the product has to be anodised. Due to the heat input during welding the mechanical properties will be reduced by approximately 50% (ref. EN1999-1).

Machining characteristics¹: T4 Temper 3 / T5, T6 Temper 2

Coating properties¹ Hard/protective anodising: 1 / Decorative / bright / colour anodising: 2

Corrosion resistance¹ General: 1 Marine: 2

¹Relative qualification ranging from 1-very good to 6-unsuitable