

MOX Systems - tækniskjöl

datasheet-gravity-en.pdf

Tæknileg þýðing: skoðaðu upprunalegu teikningarnar og tilvísunarsíður fyrir mál.

Heimildasíða 1

Vörugagnablað

Framleiðandi Mox Profile Systems

Heiti skjals Hönnun og gæði: Gravity

Vöruheiti Gravity

Vörulýsing áli skirt Board Profile

Vörunúmer GRV

Notkunarsvæði Almennur, skrifstofa, íbúðarhúsnæði

Efni EN AW 6463 T6, EN AW 6061 T6

Lengd 2500mm

Yfirborð anodized

Gravity álplötur er sérhannað snið sem er fest við neðri brúnir veggisins og gefur teppalögðum svæðum snyrtilegt og hreint yfirbragð.

Gravity álborðasnið veitir ekki aðeins óaðfinnanleg umskipti milli gólfs og veggs, heldur veitir teppabrúnirnar einnig vernd.

Það er einstaklega endingargott og endingargott þar sem það er framleitt úr hágæða hráefni og hefur þykka vegg.

Ólíkt keppinautum sínum sker hann sig úr með þykkt lagsins og gæðum anodizing.

Gravity veitir fullkomna umskipti við gólfíð.

Veggklæðningar úr gifsplötu eða keramik eru settar á sniðið og mynda þannig útlit sem jafnast við vegginn.

Auðvelt er að setja Gravity álborðssnið með því að setja flísalím á samskeytin.

Hægt er að setja saman horn með því að klippa snið í 45 gráður.

Gravity álplötur eru með matti anodized húðun í silfurlitum.

Síða 1/2

Ábyrgð

Þessi vara er í ábyrgð í 5 ár frá móttökudegi nema fyrir notendavillur eins og taldar eru upp hér að neðan:

Skemmdir af völdum höggs Skemmdir af völdum klóra. Skemmdir af völdum slípiefna eða efnahreinsiefna í snertingu við snertingu við efnahreinsiefni. Skemmdir af völdum langvarandi snertingar við vatn.

Skemmdir af völdum mikils hitastigs. Skemmdir af völdum uppsetningar

LANOITANRETNÍ FORANODISING QUALITYLABEL INDUSTRIAL TS-EN 755-8 TS-EN 755-9 TS 4922

Heimildasíða 2

ALLOY gagnablað

EN AW 6463 T6 [AlMg0.7Si]

Notkunarstaður

Málblönduna EN AW-6463 er mikið notað útpressunarálfelgur, hentugur fyrir notkun þar sem aðeins er krafist lítils styrkleika.

Hlutar geta verið

framleitt með góðum yfirborðsgæðum, hentugur fyrir margar húðunaraðgerðir.

Dæmigert notkunarsvið eru húsgögn, frágangsefni, gluggar og hurðir, frágangur á yfirbyggingu bíla, framhliðargerð, ljósasúlur og fánastöng.

Efnasamsetning samkvæmt EN573-3 (þyngd%, afgangur Al)

Si Fe Cu Mn Mg Cr Zn Ti Al

0,20 - 0,60 Max 0,15 0,2 Max 0,5 0,45 - 0,9 - Max 0,05 Max 0,1 Rest

Vélrænir eiginleikar samkvæmt EN755-2

Temper* Veggþykkt e*** Afkastaspenna Togstyrkur Lenging Brinell hörku

- e* mm Rp0,2 mín Mpa Rm mín Mpa Min A50mm % - Hámark A % HB**

T4 e≤50 75 125 14 - 12 46

T5 e≤50 150 110 8 - 6 60

T6 e≤50 195 160 10 - 8 74

* Herðaheiti í samræmi við EN515: T4-Náttúrulega eldað í stöðugt ástand, T5-kælt frá háhitamyndun og tilbúnað öldrun, T6-lausn hitameðhöndluð, slökkt og tilbúinn öldrun,

** Hörkugildin eru aðeins til vísbendinga,

*** Fyrir mismunandi veggþykkt innan eins sniðs skulu lægstu tilgreindir eiginleikar taldir gilda fyrir allt sniðið.

Eðliseiginleikar (áætluð gildi, 20°C)

Eðlismassi Bræðslusvið Rafmagns hitastuðull af stuðull af

(kg/m³) (°C) leiðni leiðni hitateygjanleiki

2700 585-650 (MS/m) (W/m.K) stækkun (GPa)

28-34 200-220 10⁻⁶/K ~70

Suðuhæfni¹

Gas: 3 TIG: 2 MIG: 2

Dæmigert fylliefni (EN ISO18273): SG-AlMg5Cr(A) eða AlSi5 og AlMg3 þegar rafskauta þarf vöruna.

Vegna hitainntaksins við suðu er

vélrænni eiginleikar munu minnka um það bil 50% (sbr.

EN1999-1).

Vinnslueiginleikar¹: T4 Temper 3 / T5, T6 Temper 2

Húðunareiginleikar¹ Harð/hlíðar rafskaut: 1 / Skreytingar / björt / litar rafskaut: 2

Tæringarþol¹ Almennt: 1 Marine: 2

¹Hlutfallslegt hæfi, allt frá 1-mjög gott til 6-óhentugt

Síða 2/2

Upprunalegar teikningar og tilvísunarsíður

Product Datasheet



Manufacturer	Mox Profile Systems
Document Title	Design and quality: Gravity
Product Name	Gravity
Product Description	Aluminium Skirting Board Profile
Item No	GRV
Area of Use	Public, Office, Residential
Material	EN AW 6463 T6, EN AW 6061 T6
Length	2500mm
Surface	Anodised

Gravity aluminum skirting board is a specially designed profile that is attached to the lower edges of the wall and provide a neat and clean appearance to carpeted areas. Gravity aluminum skirting board profile not only provides a seamless transition between the floor and the wall, but also provides protection for carpet edges. It is extremely durable and long-lasting since it is produced from high quality raw material and has thick walls. Unlike its competitors, it stands out with its coating thickness and quality of anodizing. Gravity provides a perfect transition with the floor. Plasterboard or ceramic wall coverings are applied on the profile, creating a flush appearance with the wall. Gravity aluminum skirting board profile can be easily installed by applying tile adhesive to the joints extensions. Corners can be assembled by cutting profile to 45 degree. Gravity aluminum skirting board has a matte anodized coating option in silver color.



Warranty

This product is under warranty for 5 years from the date of receipt except for the user errors as listed below:

- Damage caused by impact
- Damage caused by scratching
- Damage caused by abrasive substance or chemical cleaning agents contact
- Damage caused by prolonged contact with water
- Damage caused by exposure to intense temperature
- Damage caused by montage



ALLOY DATASHEET

EN AW 6463 T6 [AlMg0.7Si]

Place Of Use

The alloy EN AW-6463 is a widely used extrusion alloy, suitable for applications where only modest strength properties are required. Parts can be produced with a good surface quality, suitable for many coating operations. Typical application fields are furniture, finishing materials, windows and doors, car body finishing, facade construction, lighting columns and flagpoles.

Chemical composition according to EN573-3 (weight%, remainder Al)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0,20 - 0,60	Max 0,15	0,2	Max 0,5	0,45 - 0,9	-	Max 0,05	Max 0,1	Rest

Mechanical properties according to EN755-2

Temper*	Wall Thickness e***	Yield Stress	Tensile Strength	Elongation	Brinell Hardness
-	e* mm	Rp0,2 min Mpa	Rm min Mpa	Min A50mm % - Max A %	HB**
T4	e≤50	75	125	14 - 12	46
T5	e≤50	150	110	8 - 6	60
T6	e≤50	195	160	10 - 8	74

* Temper designation according to EN515: T4-Naturally aged to a stable condition, T5-cooled from an elevated temperature forming operation and artificially aged, T6-Solution heat treated, quenched and artificially aged,

** Hardness values are for indication only,

*** For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section.

Physical properties (approximate values, 20°C)

Density (kg/m³)	Melting range (°C)	Electrical conductivity (MS/m)	Thermal conductivity (W/m.K)	Co-efficient of thermal expansion	Modulus of elasticity (GPa)
2700	585-650	28-34	200-220	10 ⁻⁶ /K 23.4	~70

Weldability¹

Gas: 3 TIG: 2 MIG: 2

Typical filler materials (EN ISO18273): SG-AlMg5Cr(A) or AlSi5, and AlMg3 when the product has to be anodised. Due to the heat input during welding the mechanical properties will be reduced by approximately 50% (ref. EN1999-1).

Machining characteristics¹: T4 Temper 3 / T5, T6 Temper 2

Coating properties¹ Hard/protective anodising: 1 / Decorative / bright / colour anodising: 2

Corrosion resistance¹ General: 1 Marine: 2

¹Relative qualification ranging from 1-very good to 6-unsuitable