
# **Product Datasheet**



Manufacturer	Mox Profile Systems
Document Title	Design and quality: Visio
Product Name	Visio
Product Description	Aluminium Carpet Threshold Profile
Item No	VSO
Area of Use	Public, Office, Residential
Material	EN AW 6463 T6, EN AW 6061 T6
Length	2500mm
Surface	Anodised

Visio aluminum carpet threshold profile provides safe, aesthetic and long-lasting interior transitions between different flooring materials. It creates a safe environment, especially for children and the elderly, by providing a smooth transition between different flooring heights. Visio aluminum carpet threshold profile is designed to close gaps between carpet and other floor coverings. It provides a smooth transition between carpet and other floor covering types, eliminating any irregularities or tripping hazards that may occur. It also prolongs the life of carpets by protecting them against wear and tear. Visio, which has an aesthetic appearance as well as functional advantages, improves the overall appearance of your interior design. It is extremely durable and long-lasting since it is produced from high quality raw material and has thick walls. Unlike its competitors, it stands out with its coating thickness and quality of anodizing. While it provides a modern appearance with its serrated design, it prevents unwanted accidents thanks to its non-slip feature. At the same time, its oval design helps hide defects at floor joints. Visio aluminum carpet threshold profile can be easily installed by applying tile adhesive to the joints extensions. Corners can be assembled by cutting profile to 45 degree. Visio aluminum carpet threshold profile has a matte anodized coating option in silver, yellow and inox colors.





## Warranty

This product is under warranty for 5 years from the date of receipt except for the user errors as listed below:

Damage caused by impact

Damage caused by scratching

Damage caused by abrasive substance or chemical cleaning agents contact

Damage caused by prolonged contact with water Damage caused by exposure to intense temperature Damage caused by montage











## ALLOY DATASHEET EN AW 6463 T6 [AlMq0.7Si]

#### Place Of Use

The alloy EN AW-6463 is a widely used extrusion alloy, suitable for applications where only modest strength properties are required. Parts can be produced with a good surface quality, suitable for many coating operations. Typical application fields are furniture, finishing materials, windows and doors, car body finishing, facade construction, lighting columns and flagpoles.

### Chemical composition according to EN573-3 (weight%, remainder Al)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0,20 - 0,60	Max 0,15	0,2	Max 0,5	0,45 - 0,9	-	Max 0,05	Max 0,1	Rest

#### Mechanical properties according to EN755-2

Temper*	Wall Thickness e*** e* mm	Yield Stress Rp0,2 min Mpa	Tensile Strength Rm min Mpa	Elongation Min A50mm % - Max A %	Brinell Hardness HB**
T4	e≤50	75	125	14 - 12	46
T5	e≤50	150	110	8 - 6	60
Т6	e≤50	195	160	10 - 8	74

<sup>\*</sup> Temper designation according to EN515: T4-Naturally aged to a stable condition, T5-cooled from an elevated temperature forming operation and artificially aged, T6-Solution heat treated, quenched and artificially aged,

## Physical properties (approximate values, 20°C)

Density (kg/m³) 2700	Melting range (°C) 585-650	Electrical conductivity (MS/m) 28-34	Thermal conductivity (W/m.K) 200-220	Co-efficient of thermal expansion 10-6/K 23.4	Modulus of elasticity (GPa) ~70
----------------------------	----------------------------------	---	---	---	--

### Weldability<sup>1</sup>

Gas: 3 TIG: 2 MIG: 2

Typical filler materials (EN ISO18273): SG-AIMg5Cr(A) or AISi5, and AIMg3 when the product has to be anodised. Due to the heat input during welding the mechanical properties will be redured by approximately 50% (ref. EN1999-1).

Machining characteristics<sup>1</sup>: T4 Temper 3 / T5, T6 Temper 2

Coating properties<sup>1</sup> Hard/protective anodising: 1 / Decorative / bright / colour anodising: 2

Corrosion resistance<sup>1</sup> General: 1 Marine: 2

<sup>1</sup>Relative qualification ranging from 1-very good to 6-unsuitable

<sup>\*\*</sup> Hardness values are for indication only,

<sup>\*\*\*</sup> For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section.