

MOX Systems - technická dokumentácia

datasheet-wishled-us-en.pdf

Technický preklad: rozmery nájdete na pôvodných výkresoch a referenčných stránkach.

Zdrojová stránka 1

Produktový list

Výrobca Mox Profile Systems

Názov dokumentu Dizajn a kvalita: Wishled

Názov produktu Wishled

Popis produktu Vzorovaná hliníková LED lišta

Položka č. WSL

Oblasť použitia Verejné, kancelárske, obytné

Materiál EN AW 6463 T6, EN AW 6061 T6

Dĺžka 8'

Povrch s práškovým nástrekom, eloxovaný, chrómovaný

Hliníková LED lišta WishLED sa hodí do akéhokoľvek prostredia vďaka svojim neobmedzeným možnostiam vzorov.

Najviac sa uprednostňuje ako nočné osvetlenie v detských izbách s vymeniteľným dizajnovým potlačeným krytom.

Dá sa využiť aj na reklamu a prezentáciu firemnej identity vo verejných priestoroch.

Okrem osvetľovacej funkcie pokrýva aj chyby v spojach podlahy a stien.

Zabraňuje hromadeniu nečistôt a škodlivým organizmom a poskytuje hygienické a zdravé používanie po mnoho rokov.

Vďaka dutej oblasti vo svojom dizajne zhromažďuje telefónne, elektrické a internetové káble, aby organizoval vaše prostredie.

Je mimoriadne odolný a má dlhú životnosť, pretože je vyrobený z vysoko kvalitných surovín a má hrubé steny.

Na rozdiel od svojich konkurentov vyniká hrúbkou povlaku a kvalitou eloxovania a aplikáciou predbežnej úpravy, ktorá poskytuje odolnosť proti korózii pri elektrostatickom práškovom lakovaní.

Horný a spodný rám WishLED sú hliníkové a v strede majú dizajnový panel s potlačou, ktorý je možné podľa chuti vymeniť.

Hliníková LED lišta WishLED sa dá ľahko nainštalovať pripevnením profilu karosérie k stene pomocou skrutiek a inštaláciou LED pásikov a ovládača dovnútra.

Aplikácia bude dokončená montážou predného dizajnového potlačeného difúzneho panelu so systémom snap lock.

S vnútornými, vonkajšími a koncovými kryciami krytkami, ktoré majú rovnakú farbu ako profily, je možné ľahko aplikovať hladké rohové zákruty bez potreby šikmého rezu.

Rohové kryty tiež zabraňujú chybám osvetlenia.

Vzorovaná hliníková LED lišta WishLED má možnosti matného eloxovania, svetlého eloxu, saténovo chemicky jasne eloxovaného a elektrostatického práškového lakovania.

Zatiaľ čo sú k dispozícii strieborné, žlté, inoxové, bronzové a čierne eloxované farebné nátery, môže byť tiež lakovaný podľa požadovaného RAL kódu pomocou elektrostatického práškového lakovania.

Okrem existujúcich vzorov, ktoré ponúkame pre panel iluminátora, je možné použiť aj personalizované vzory.

Strana 1/3

Záruka

Na tento produkt sa vzťahuje záruka 5 rokov od dátumu prevzatia, s výnimkou používateľských chýb uvedených nižšie:

Damage caused by impact Damage caused by scratching Damage caused by abrasive substance or chemical cleaning agents contact Damage caused by prolonged contact with water Damage caused by exposure to intense temperature Damage caused by montage

LANOITANRETNİ FORANODISING LABEL KVALITY PRIEMYSELNÝ TS-EN 755-8 TS-EN 755-9 TS 4922

Zdrojová stránka 2

TECHNICKÝ LIST ZLIATINY

EN AW 6463 T6 [AlMg0,7Si]

Miesto použitia

Zliatina EN AW-6463 je široko používaná extrúzna zliatina, vhodná pre aplikácie, kde sa vyžadujú len nízke pevnostné vlastnosti.

Časti môžu byť

vyrobené s dobrou kvalitou povrchu, vhodné pre mnohé náterové operácie.

Typické oblasti použitia sú nábytok, dokončovacie materiály, okná a dvere,

úprava karosérie, konštrukcia fasády, stĺpy osvetlenia a stožiare.

Chemické zloženie podľa EN573-3 (hmotn. %, zvyšok Al)

Si Fe Cu Mn Mg Cr Zn Ti Al

0,20 - 0,60 Max 0,15 0,2 Max 0,5 0,45 - 0,9 - Max 0,05 Max 0,1 Odpoč.

Mechanické vlastnosti podľa EN755-2

Temper* Hrúbka steny e*** Medza klzu Pevnosť v ťahu Predĺženie Tvrdosť podľa Brinella

- e* mm Rp0,2 min Mpa Rm min Mpa Min A50 mm % - Max A % HB**

T4 e≤50 75 125 14 - 12 46

T5 e≤50 150 110 8 - 6 60

T6 e≤50 195 160 10 - 8 74

* Označenie teploty podľa EN515: T4-Prirodzene zostarnuté do stabilného stavu, T5-chladené z operácie tvárnenia pri zvýšenej teplote a

umelo starnúce, T6-Solution tepelne spracované, kalené a umelo starnuté,

** Hodnoty tvrdosti sú len orientačné,

*** For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section.

Fyzikálne vlastnosti (približné hodnoty, 20°C)

Hustota Rozsah topenia Elektrický tepelný súčiniteľ modulu

(kg/m³) (°C) vodivosť vodivosť tepelná elasticita

2700 585-650 (MS/m) (W/m.K) rozšírenie (GPa)

28-34 200-220 10⁻⁶/K ~70

Zvárateľnosť¹

Plyn: 3 TIG: 2 MIG: 2

Typické výplňové materiály (EN ISO18273): SG-AlMg5Cr(A) alebo AlSi5, a AlMg3, ak má byť produkt eloxovaný.

V dôsledku tepelného príkonu pri zváraní

mechanické vlastnosti sa znížia približne o 50 % (ref.

EN1999-1).

Vlastnosti obrábania¹: T4 Temper 3 / T5, T6 Temper 2

Vlastnosti povlaku¹ Tvrdé/ochranné eloxovanie: 1 / Dekoratívne / svetlé / farebné eloxovanie: 2

Odolnosť proti korózii¹ Všeobecne: 1 Námorná: 2

¹Relatívna kvalifikácia v rozsahu od 1 - veľmi dobré po 6 - nevhodné

Strana 2/3

Zdrojová stránka 3

Pvc transparentný LED difúzny pás

Meracia páska, bez uhla Meracia páska, č

Tolerancie píly Tolerancie píly (priamy rez)

test skúšobného uhla

DIN 16941:2021-11 Tolerancia kruhového priemeru a výšky skosenia (mm) DIN 16941:2021-11 4
Tolerancia skreslenia TV

Séria tolerancií 3 3-6 6-10 10-18 30-50 50-80 >50 Tolerancia Line <30 30-60 60-120 120-180 180-250
>250

2A a 2B $\pm 0,5$ $\pm 20\%$ $\pm 18\%$ $\pm 15\%$ $\pm 15\%$ $\pm 12\%$ $\pm 10\%$ 2A, 3A, 4A 5° 4° 3°30' 3° 2°30' 2°

Rozsah menovitých veľkostí DIN 16941: 2021-11 (mm)

Tolerancia hrúbky steny Tolerancie dĺžkových meraní

Séria tolerancie

2A a 2B $\pm 0,2$ $\pm 0,3$ $\pm 0,4$ $\pm 0,5$ $\pm 0,6$ $\pm 0,8$ % $\pm 0,3$ $\pm 0,4$ $\pm 0,5$ $\pm 0,6$ $\pm 0,7$ $\pm 0,8$ $\pm 1,0$ $\pm 1,2$ $\pm 2,0$ $\pm 3,0$

Strana 3/3


Originálne výkresy a referenčné strany

Product Datasheet



Manufacturer	Mox Profile Systems
Document Title	Design and quality: Wishled
Product Name	Wishled
Product Description	Patterned Aluminium LED Skirting Board
Item No	WSL
Area of Use	Public, Office, Residential
Material	EN AW 6463 T6, EN AW 6061 T6
Length	8'
Surface	Powder Coated, Anodised, Chrome Plated

WishLED aluminium LED skirting board can match with any environment due to its unlimited pattern designs options. It is mostly preferred as night lighting in children's rooms with its replaceable design printed cover. It can also be used for advertising and to present corporate identity in public areas. In addition to its illumination feature, it also covers the defects in floor and wall joints. It prevents dirt accumulation and harmful organisms to provide hygienic and healthy use for many years. With the hollow area in its design, it collects the telephone, electricity and internet cables to organize your environment. It is extremely durable and long-lasting since it is produced from high quality raw material and has thick walls. Unlike its competitors, it stands out with its coating thickness and quality of anodizing, and with its pretreatment application that provides resistance to corrosion in electrostatic powder painting. WishLED's upper and lower frames are aluminium and has design printed panel in the middle that can be replaced according to taste. WishLED aluminium LED skirting board can be easily installed by fixing the body profile to wall with screws and installing the LED strips and driver inside. Application will be completed by mounting the front design printed diffuser panel with its snap lock system. With the inner, outer and end covering caps, which are the same color as the profiles, smooth corner turns can be easily applied without the need for an angled cut. Corner caps also prevent lighting flaws. WishLED patterned aluminium LED skirting board has matte anodized, bright anodized, satin chemical bright anodized and electrostatic powder painting options. While silver, yellow, inox, bronze and black anodized color coatings are available, it can also be painted to the desired RAL code with electrostatic powder painting. In addition to existing pattern designs we offer for the illuminator panel, personalized designs can also be applied.



Warranty

This product is under warranty for 5 years from the date of receipt except for the user errors as listed below:

- Damage caused by impact
- Damage caused by scratching
- Damage caused by abrasive substance or chemical cleaning agents contact
- Damage caused by prolonged contact with water
- Damage caused by exposure to intense temperature
- Damage caused by montage



ALLOY DATASHEET

EN AW 6463 T6 [AlMg0.7Si]

Place Of Use

The alloy EN AW-6463 is a widely used extrusion alloy, suitable for applications where only modest strength properties are required. Parts can be produced with a good surface quality, suitable for many coating operations. Typical application fields are furniture, finishing materials, windows and doors, car body finishing, facade construction, lighting columns and flagpoles.

Chemical composition according to EN573-3 (weight%, remainder Al)

Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Al
0,20 - 0,60	Max 0,15	0,2	Max 0,5	0,45 - 0,9	-	Max 0,05	Max 0,1	Rest

Mechanical properties according to EN755-2

Temper*	Wall Thickness e***	Yield Stress	Tensile Strength	Elongation	Brinell Hardness
-	e* mm	Rp0,2 min Mpa	Rm min Mpa	Min A50mm % - Max A %	HB**
T4	e≤50	75	125	14 - 12	46
T5	e≤50	150	110	8 - 6	60
T6	e≤50	195	160	10 - 8	74

* Temper designation according to EN515: T4-Naturally aged to a stable condition, T5-cooled from an elevated temperature forming operation and artificially aged, T6-Solution heat treated, quenched and artificially aged,

** Hardness values are for indication only,

*** For different wall thicknesses within one profile, the lowest specified properties shall be considered as valid for the whole profile cross section.

Physical properties (approximate values, 20°C)

Density (kg/m³)	Melting range (°C)	Electrical conductivity (MS/m)	Thermal conductivity (W/m.K)	Co-efficient of thermal expansion 10 ⁻⁶ /K	Modulus of elasticity (GPa)
2700	585-650	28-34	200-220	23.4	~70

Weldability¹

Gas: 3 TIG: 2 MIG: 2

Typical filler materials (EN ISO18273): SG-AlMg5Cr(A) or AlSi5, and AlMg3 when the product has to be anodised. Due to the heat input during welding the mechanical properties will be reduced by approximately 50% (ref. EN1999-1).

Machining characteristics¹: T4 Temper 3 / T5, T6 Temper 2

Coating properties¹ Hard/protective anodising: 1 / Decorative / bright / colour anodising: 2

Corrosion resistance¹ General: 1 Marine: 2

¹Relative qualification ranging from 1-very good to 6-unsuitable

Pvc Transparent Led Diffuser Strip

Saw Tolerances							Measuring tape, no angle test	Saw Tolerances (Inline Cut)							Measuring tape, no angle test
<500	>500	>1000	>1500	>2000	>3000	>4000	>4500	<500	>500	>1000	>1500	>2000	>3000	>4000	>4500
±0.3	±0.5	±1.0	±1.5	±2.0	±3.0	±4.0	±0.1%	±0.3	±0.5	±1.0	±1.5	±2.0	±3.0	±4.0	±0.1%

DIN 16941:2021-11	Tolerance of the circular diameter and chamfer heights (mm)							DIN 16941:2021-11	4 Distortion tolerance TV					
Tolerance Series	3	3-6	6-10	10-18	30-50	50-80	>50	Tolerance Line	<30	30-60	60-120	120-180	180-250	>250
2A & 2B	±0.5	±20%	±18%	±15%	±15%	±12%	±10%	2A, 3A, 4A	5°	4°	3°30'	3°	2°30'	2°

DIN 16941:2021-11	Nominal Size Range (mm)															
Tolerance Series	Tolerance of wall thickness						Tolerances of length measurements									
	1.2	1.2-2.5	2.5-4	4-6.5	6.5-10	>10	<3	3-6	6-10	10-18	18-30	30-50	50-80	80-120	120-250	250-400
2A & 2B	±0.2	±0.3	±0.4	±0.5	±0.6	±0.8%	±0.3	±0.4	±0.5	±0.6	±0.7	±0.8	±1.0	±1.2	±2.0	±3.0

